

SUBMITTAL SHEET (effective 19AUG18)

Polymer Base: Neoprene (CR Based)

F-02011 (Black)

Physical Properties	Unit	Test Method	Typical Results
Density	g/cm ³	ASTM D 1056	0.144 ± 0.032
	lb/ft ³	ASTM D 1056	9 ± 2
Hardness, Durometer Shore 00		ASTM D 2240	45 ± 5
Compression Deflection (25%)	kPa	ASTM D 1056	24 ± 10
	psi	ASTM D 1056	3.5 ± 1.5
Compression Set	%	ASTM D 1056	≤ 25%
Tensile Strength	kPa	ASTM D 412 (Die A)	520
	psi	ASTM D 412 (Die A)	75
Tear Strength	kN/m	ASTM D 624 (Die C)	3.3
	lb/in	ASTM D 624 (Die C)	12
Elongation	%	ASTM D 412 (Die A)	150%
Resilience	%	ASTM D 2632	30%
Service Temperature			
Low	°F	ASTM D 1056	-40
High Continuous	°F		150
High Intermittent	°F		200
Water Absorption			
Maximum Weight Change	%	ASTM D 1056	≤5%
Fluid Immersion (7 days at 23°C [73.4°F])			
ASTM Ref. Fuel B, Weight Change (%)	%	ASTM D 1056	Not applicable
Accelerated Aging (7 days at 70°C [158°F])			
Flexibility (180° bend without cracking)			Pass
Appearance change			None
Change in Compression Deflection	%	ASTM D 1056	+ 30%
Combustion Characteristics		FMVSS-302	Pass at 0.125" (1/8") (3.1 mm) and higher

ASTM D 1056-14 designation: 2A1
SAE J 18 APR2002 designation: 2A1
ASTM D 6576-13: II **A/B Soft**

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 7600 Oakwood Street Ext. • Mebane NC 27302
email: info.cf.us@armacell.com • www.armacell.us

Mebane, NC • 919-304-3846 ext 3934
Spencer, WV • 800-638-6312

© 2018 Armacell LLC

F-02011	01	08	18	NA	NA
---------	----	----	----	----	----

