

SOLUTIONS FOR ENERGY SAVINGS

AP ArmaFlex[®]

Black Lap Seal

The original flexible elastomeric pipe insulation with a lap seal for greater seam security and increased protection against condensation, mold and energy loss.

- // Durable, low-profile lap seal with wider release tab, stays closed and looks neat
- // Easy to install – an excellent choice for retrofit applications
- // 25/50 rated for use in air plenums
- // Fiber-free, formaldehyde-free, low VOC and non-particulating

www.armacell.us



 **armacell**[®]
ArmaFlex[®]

TECHNICAL DATA – AP ArmaFlex® BLACK LAPSEAL TUBE INSULATION

Description

Black flexible closed-cell elastomeric thermal insulation in tubular form with a self-seal system reinforced with lap seal tape

Applications

Insulation for piping associated with HVAC, VRV and VRF systems, chillers, hot and cold water, refrigeration. For use in commercial, industrial, and residential applications.

Specification Compliance

ASTM C 534, Type I – Grade 1 ASTM E 84	UL 723 NFPA 90A, 90B	UL 181 ASTM G21/C1338	ASTM D 1056, 2C1
---	-------------------------	--------------------------	------------------

Approvals, Certifications, Compliances

- 3rd party certified by FM Approvals through 1-1/2" wall thickness per FM 4924
- GREENGUARD® Gold Certified.
- Manufactured without CFCs, HFCs, HCFCs, PBDEs, or Formaldehyde.
- Made with EPA registered Microban® antimicrobial product protection.
- All Armacell facilities in North America are ISO 9001 certified.
- Plenum Rated
- Conforms to ASHRAE 90.1 Energy Standards
- Conforms to building codes: International Mechanical Code, IMC, International Energy Conservation Code, IECC, International Residential Code, IRC, Title 24 California Building Energy Efficiency Standards.

Typical Properties

Specifications	Values		Test Method
	3/8" through 1" Wall (NBR/PVC based)	1-1/2" and 2" Walls (EPDM based)	
Thermal Conductivity: Btu • in/h • ft ² • °F (W/mK)			
50°F Mean Temperature (10°C)	0.235 (0.034)	0.278 (0.040)	ASTM C 177 or C 518
75°F Mean Temperature (24°C)	0.245 (0.0353)	0.28 (0.040)	
100°F Mean Temperature (38°C)	0.257 (0.037)	0.289 (0.041)	
125°F Mean Temperature (52°C)	0.268 (0.039)	0.300 (0.043)	
Water Vapor Permeability: Perm-in. [Kg/(s • m • Pa)]	0.05 (0.725 x 10 ⁻¹³)	0.08 (1.16 x 10 ⁻¹³)	ASTM E 96, Procedure A
Flame Spread and Smoke Developed Index:	25/50 rated	25/50 rated	ASTM E 84, UL 723
Water Absorption, % by Volume:	0.2 %	0.2 %	ASTM C 209 or ASTM C1763
Mold Growth: Fungi Resistance:	Passed	Passed	UL181 ASTM G21/C1338
Maximum Service Temperature	220°F (105°C) ①	300°F (149°C) ②	ASTM C534
Minimum Service Temperature ③	-297°F (-183°C) ④	-297°F (-183°C) ④	ASTM C534

Sizes

Wall Thickness (nominal) Form	3/8", 1/2", 3/4" 1", 1-1/2", 2" (10, 13, 19, 25, 38, 50 mm)
Inside Diameter, Tubular Form	3/8" ID to 6" ID (10 mm to 153 mm) [3/8" and 1/2" IDs not offered in 3/8" wall thickness]
Length of Sections, Tubular Form	6' (1.8 m)

Outdoor Use

Painting with WB Finish or other protective jacketing is required to prevent damage to the insulation in exterior applications and to comply with the insulation protection sections of the International Energy Conservation Code (IECC) and ASHRAE 90.1.

- ① AP ArmaFlex BST Pipe Insulation can withstand temperatures as high as 250°F for 96 hour time periods when tested according to ASTM C411 - Standard Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation.
- ② 1-1/2" and 2" AP ArmaFlex tubes are formulated with EPDM rubber giving them a higher upper use temperature than AP ArmaFlex tubes less than 1-1/2" wall thickness.
- ③ At temperatures below -20°F (-29°C), elastomeric insulation starts to become less flexible. However, this characteristic does not affect thermal efficiency and resistance to water vapor permeability of ArmaFlex insulation.
- ④ For applications of -40°F to -297°F (-40°C to -183°C), contact Armacell



GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

Microban antimicrobial product protection is limited to the product itself and is not designed to protect the users of these products from disease causing microorganisms, or as a substitute for normal cleaning and hygiene practices. Microban International, Ltd. makes neither direct nor implied health claims for the products containing Microban® antimicrobial product protection. Data, photomicrographs and information presented are based on standard laboratory tests and are provided for comparative purposes to substantiate antimicrobial activity for non-public health uses. Microban is a registered trademark of Microban International, Ltd.

AP ArmaFlex BLACK LAPSEAL TUBE INSULATION - R VALUES

3/8 " Walls

IPBST05838	1/2" Copper	2.6
IPBST03438	5/8" Copper	2.4
IPBST07838	3/4" Copper	2.4
IPBST11838	1" Copper	2.3
IPBST13838	1-1/4" Copper	2.2
IPBST15838	1-1/2" Copper	2.5
IPBST11038	1-1/2" IPS	2.4
IPBST21838	2" Copper	2.4

1/2 " WALLS

IPBST03812	1/4" Copper	3.3
IPBST01212	3/8" Copper	3.3
IPBST05812	1/2" Copper	3.4
IPBST03412	5/8" Copper	3.3
IPBST07812	3/4" Copper	3.3
IPBST11812	1" Copper	3.3
IPBST13812	1-1/4" Copper	3.2
IPBST15812	1-1/2" Copper	3.2
IPBST11012	1-1/2" IPS	3.1
IPBST21812	2" Copper	3.2
IPBST20012	2" IPS	3.2
IPBST25812	2-1/2" Copper	3.2
IPBST21012	2-1/2" IPS	3.2
IPBST31812	3" Copper	3.2
IPBST30012	3" IPS	3.1
IPBST35812	3-1/2" Copper	3.1
IPBST41812	4" Copper	3.1
IPBST40012	4" IPS	3.0

3/4 " WALLS

IPBST03834	1/4" Copper	5.9
IPBST01234	3/8" Copper	5.5
IPBST05834	1/2" Copper	5.6
IPBST03434	5/8" Copper	5.5
IPBST07834	3/4" Copper	5.4
IPBST11834	1" Copper	5.4
IPBST13834	1-1/4" Copper	5.3
IPBST15834	1-1/2" Copper	5.1
IPBST11034	1 1/2" IPS	4.9
IPBST21834	2" Copper	4.8
IPBST20034	2" IPS	5.2
IPBST25834	2-1/2" Copper	4.7
IPBST21034	2-1/2" IPS	5.0
IPBST31834	3" Copper	4.6
IPBST30034	3" IPS	4.9
IPBST35834	3-1/2" Copper	4.5
IPBST41834	4" Copper	4.5
IPBST40034	4" IPS	4.8

1" WALLS

IPBST03810	1/4" Copper	7.3
IPBST01210	3/8" Copper	7.2
IPBST05810	1/2" Copper	7.2
IPBST03410	5/8" Copper	7.0
IPBST07810	3/4" Copper	7.0
IPBST11810	1" Copper	7.2
IPBST13810	1-1/4" Copper	7.2
IPBST15810	1-1/2" Copper	7.2
IPBST11010	1-1/2" IPS	6.9
IPBST21810	2" Copper	6.8
IPBST20010	2" IPS	7.1
IPBST25810	2-1/2" Copper	6.5
IPBST21010	2-1/2" IPS	6.8
IPBST31810	3" Copper	6.3
IPBST30010	3" IPS	6.6
IPBST35810	3-1/2" Copper	6.2
IPBST41810	4" Copper	6.1
IPBST40010	4" IPS	6.4
IPBST50010	5" IPS	6.2
IPBST60010	6" IPS	6.1

1-1/2" WALLS

IPBST03815	1/4" Copper	13.7
IPBST01215	3/8" Copper	12.7
IPBST05815	1/2" Copper	12.0
IPBST03415	5/8" Copper	11.3
IPBST07815	3/4" Copper	10.8
IPBST11815	1" Copper	10.1
IPBST13815	1-1/4" Copper	9.6
IPBST15815	1-1/2" Copper	9.2
IPBST11015	1-1/2" IPS	8.7
IPBST21815	2" Copper	8.6
IPBST20015	2" IPS	8.8
IPBST25815	2-1/2" Copper	8.2
IPBST21015	2-1/2" IPS	8.4
IPBST31815	3" Copper	7.9
IPBST30015	3" IPS	8.1
IPBST35815	3-1/2" Copper	7.7
IPBST41815	4" Copper	7.5
IPBST40015	4" IPS	7.8
IPBST50015	5" IPS	7.5
IPBST60015	6" IPS	7.3

2" WALLS

IPBST03820	1/4" Copper	19.7
IPBST01220	3/8" Copper	18.2
IPBST05820	1/2" Copper	17.2
IPBST03420	5/8" Copper	16.2
IPBST07820	3/4" Copper	15.5
IPBST11820	1" Copper	14.5
IPBST13820	1-1/4" Copper	13.7
IPBST15820	1-1/2" Copper	13.1
IPBST11020	1-1/2" IPS	12.4
IPBST21820	2" Copper	12.2
IPBST20020	2" IPS	12.3
IPBST25820	2-1/2" Copper	11.6
IPBST21020	2-1/2" IPS	11.7
IPBST31820	3" Copper	11.1
IPBST30020	3" IPS	11.2
IPBST35820	3-1/2" Copper	10.7
IPBST41820	4" Copper	10.5
IPBST40020	4" IPS	10.7
IPBST50020	5" IPS	10.2
IPBST60020	6" IPS	9.9

* These specifications are based on the measurement methods employed by Armacell. Other methods may not result in the same values and cannot be used to determine if the product is within the given tolerance.

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2021. All rights reserved. Trademarks followed by ® or TM are trademarks of the Armacell Group.
AP ArmaFlex | Black LapSeal Tube TDS | 112021 | NA | EN-A | 020

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,000 employees and 23 production plants in 15 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:
www.armacell.us
800-866-5638

