

DRIVEN BY PERFORMANCE

Monarch[®] 5011

Closed cell EPDM/CR/SBR blend foam in bun form

- // ASTM D 1056 2A1/2A2
- // Manufactured in buns (blocks)
- // UL Listed: UL94 HF-1
- // Added flame retardant

www.armacell.us



 **armacell**[®]
ArmaComp[™]

MONARCH 5011 | Closed cell EPDM/CR/SBR blend foam in bun form

Monarch 5011: Armacell (Spencer, WV Plant) manufactures a black, closed cell, 7 - 11 lb/ft³ (112 - 176 kg/m³) density, EPDM/CR/SBR blended rubber product 5011, that meets the requirements of ASTM D 1056 2A1/2A2. 5011 incorporates a flame retardant and is listed with UL to UL94 HF-1 (UL File #: QMFZ2.E55798) at 1.6 mm (0.063") and higher. 5011 meets the horizontal burn/flame requirements of FMVSS 302, 4 inches per minute burn rate max., at 3.18 mm (0.125") and higher.

TECHNICAL DATA SHEET | BUNS (effective 12/7/2022)

POLYMER: EPDM/CR/SBR

Physical Property	Test Method	Unit	Value	
ASTM D 1056 Designation	-	-	2A1/2A2	
Cell Structure	-	-	Closed	
Color	-	-	Black	
Compression Deflection 25%	ASTM D 1056	psi kPa	4 - 7 27.6 - 48.3	
Compression Deflection 25%, after Heat Aging	ASTM D 1056	%	± 30	
Compression Set (Room temp)	ASTM D 1056	%	40 max	
Density	ASTM D 1056	lb/ft ³ kg/m ³	7 - 11 112 - 176	
Elongation	ASTM D 412 (Die A)	%	150 min	
Flammability	FMVSS 302	in mm	0.125 and higher 3.17 and higher	
Hardness, Durometer Shore 00	ASTM D 2240	-	45 - 65	
Resilience	ASTM D 2632	%	27 - 37	
Service Temperature	Low	ASTM D 1056	°F °C	-40 -40
	High Continuous	-	°F °C	200 93.3
	High Intermittent	-	°F °C	250 212
Tear Strength	ASTM D 624 (Die C)	lb/in kN/m	10 min 1.7 min	
Tensile Strength	ASTM D 412 (Die A)	psi kPa	55 min 379 min	
Water Absorption	ASTM D 1056	%	5 max	

UL Listed to: UL94 (Flame) HF-1 (UL file# QMFZ2.E55798) at 1.6 mm minimum thickness

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2023. All rights reserved. Trademarks followed by © or TM are trademarks of the Armacell Group.
Monarch 5011 | Data Sheet | 012023 | NA | EN-A

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,100 employees and 26 production plants in 18 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:

www.armacell.us

info.cf.us@armacell.com

800-973-0490

