

# TECHNICAL DATA SHEET (effective 10/10/23)

OleTex<sup>®</sup> BKGN 200

Buns (Blocks)

Polymer: Polyethylene (PE)

Physical Property	Test Method	Unit	Value
Cell Structure	-	-	Closed
Compression Deflection 25%	ASTM D 3575	psi	4.0 - 10
	Suffix D	kPa	28 - 69
Density	ASTM D 3575	lb/ft <sup>3</sup>	1.3 - 2.5
	Suffix W	kg/m <sup>3</sup>	20.8 - 40.1

**Disclaimer:** BKGN 200 is designed for industrial packaging applications. It should not be promoted or offered for any other use other than the intended application noted. No additional testing or certifications to other specifications will be conducted by Armacell. The product must be validated by the customer in their process as supplied, and no quality claims against the material will be accepted.

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the Armacell General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.

© 2023 Armacell OleTex<sup>®</sup> is a registered trademark of the Armacell Group.

**For more information:**  
[www.armacell.us](http://www.armacell.us)  
[info.cf.us@armacell.com](mailto:info.cf.us@armacell.com)  
 800-973-0490