


ENGINEERED FOR VERSATILITY

# OleTex<sup>®</sup> CKJN 200 F

Closed cell PE crosslinked polyolefin foam in continuous rolls/sheets form

- // Chemically crosslinked
- // UL Listed: UL94 HBF
- // Tested per ASTM D 3575
- // Added flame retardant
- // Multiple colors available

[www.armacell.us](http://www.armacell.us)



 **armacell**<sup>®</sup>  
ArmaComp<sup>™</sup>

## OLETEX® CKJN 200 F | Closed cell PE crosslinked polyolefin foam in continuous rolls/sheets form

**OleTex CKJN 200 F:** Armacell (Yukon, OK Plant) manufactures a continuous, (rolls / sheets) closed cell, 1.8 - 2.2 lb/ft<sup>3</sup> (28.8 - 35.2 kg/m<sup>3</sup>) density, PE crosslinked polyolefin foam product CKJN 200 F. CKJN 200 F contains an added flame retardant and meets the requirements of FMVSS 302 at 0.250" (1/4") (6.35 mm) & higher. CKJN 200 F is listed with UL to UL94 HBF (UL94 HBF thicknesses of 6.4 mm minimum (natural color only)) (UL File #: QMFZ2.E55798). CKJN 200 F is available in a variety of colors. \*\* This product is not intended for elevated temperature applications.

### TECHNICAL DATA SHEET | ROLLS / SHEETS (effective 20DEC21)

#### POLYMER: PE

Physical Property	Test Method	Unit	Value
Cell Structure	-	-	Closed
Color	-	-	Multiple
Compression Deflection 10%	ASTM D 3575 Suffix D	psi kPa	3 - 4.5 20.7 - 31
Compression Deflection 25%	ASTM D 3575 Suffix D	psi kPa	3.6 - 6.5 24.8 - 44.8
Compression Deflection 40%	ASTM D 3575 Suffix D	psi kPa	9 - 12.5 62.1 - 86.2
Compression Deflection 50%	ASTM D 3575 Suffix D	psi kPa	12.5 - 17.5 86.2 - 120
Compression Set (Room temp)	ASTM D 3575 Suffix B	%	TBD
Density	ASTM D 3575 Suffix W	lb/ft <sup>3</sup> kg/m <sup>3</sup>	1.8 - 2.2 28.8 - 35.2
Elongation	ASTM D 3575 Suffix T	%	75 min
Flammability	FMVSS 302	in mm	0.25 and higher 6.35 and higher
Service Temperature	Low	-	-65 -54
	High Intermittent	-	210 99
Tear Strength	ASTM D 3575 Suffix T	lb/in kN/m	7.5 min 1.3 min
Tensile Strength	ASTM D 3575 Suffix T	psi kPa	25 min 172 min
Thermal Stability	ASTM D 3575 Suffix S	%	1 max
Water Absorption	ASTM D 3575 Suffix L	lb/ft <sup>2</sup>	0.1 max
		kg/m <sup>2</sup>	0.5 max

UL Listed to UL94 (Flame) HBF (UL file# QMFZ2.E55798) at 6.4 mm minimum thickness (Color: Natural)

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2022. All rights reserved. Trademarks followed by © or TM are trademarks of the Armacell Group.  
OleTex CKJN 200 F | DataSheet | 012022 | NA | EN-A

## ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,200 employees and 24 production plants in 16 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:

[www.armacell.us](http://www.armacell.us)

[info.cf.us@armacell.com](mailto:info.cf.us@armacell.com)

800-973-0490

