## DRIVEN BY PERFORMANCE

# EnsoLite® MLC-Z

Closed cell PVC/NBR foam in continuous rolls/sheets form

### // ASTM D 1056 2A1/2C1

- // Manufactured in continuous rolls/sheets
- // Fungus resistant. Tested to ASTM G21
- // Our fast-responding technical experts will help you navigate our vast product line for any application or develop innovative solutions to meet market requirements.

www.armacell.us



### ENSOLITE MLC-Z | Closed cell PVC/NBR foam in continuous rolls/sheets form

**EnsoLite MLC-Z:** Armacell (Conover, NC Plant) manufactures a black, continuous (sheets/rolls), closed cell, 3.0 - 6.5 lb/ft<sup>3</sup> (48 - 104 kg/m<sup>3</sup>) density, PVC/NBR rubber product MLC-Z, that meets the requirements of ASTM D 1056 2A1/2C1. MLC-Z meets the horizontal burn/flame requirements of FMVSS 302 at 0.250" (1/4") (6.35 mm) & higher. MLC-Z incorporates an added biocide and has been tested for fungus resistance per ASTM G21.

#### TECHNICAL DATA SHEET | ROLLS/SHEETS (effective 29MAR21)

POLYMER: PVC/NBR				
Physical Property		Test Method	Unit	Value
ASTM D 1056 Designation		-	-	2A1/2C1
Cell Structure			_	Closed
Color		-	-	Black
Compression Deflection 25%		ASTM D 1056	psi kPa	2 - 5 13.8 - 34.4
Compression Deflection 25%, after Heat Aging		ASTM D 1056	%	<u>+</u> 30
Compression Set (Room temp)		ASTM D 1056	%	40 max
Density		ASTM D 1056	lb/ft³ kg/m³	<del>3 - 6.5</del> 48.1 - 104
Elongation		ASTM D 412 (Die A)	%	150 min
Flammability		FMVSS 302	in mm	0.25 and higher 6.35 and higher
Fluid Immersion		ASTM D 1056	%	250 max
Hardness, Durometer Shore 00		ASTM D 2240	-	20 - 40
Service Temperature	Low	ASTM D 1056	°F °C	-40 -40
	High Intermittent	_	°F °C	200 93.3
Tear Strength		ASTM D 624 (Die C)	lb/in kN/m	8 min 1.4 min
Tensile Strength		ASTM D 412 (Die A)	psi kPa	40 min 276 min
Water Absorption		ASTM D 1056	%	5 max
		ASTM D 1056	%	5 max

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our Data Protection Policy.

© Armacell, 2022. All rights reserved. Trademarks followed by ® or TM are trademarks of the Armacell Group EnsoLite MLC-Z | DataSheet | 062022 | NA | EN-A

## ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,200 employees and 24 production plants in 16 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit: www.armacell.us info.cf.us@armacell.com 800-973-0490

