

INDUSTRIAL STRENGTH

# EnsoLite<sup>®</sup> IR41

Closed cell PVC/NBR/CR foam in continuous rolls/sheets form

// ASTM D 1056 2A1/2C1/2B1

// Manufactured in continuous rolls/sheets

// Available in skin 2 sides only

// UL Listed: UL94 HBF

// UL Listed: UL50E (gaskets and seals)

[www.armacell.us](http://www.armacell.us)



 **armacell**<sup>®</sup>  
ArmaComp<sup>®</sup>

## ENSOLITE IR41 | Closed cell PVC/NBR/CR foam in continuous rolls/sheets form

**EnsoLite IR41:** Armacell (Conover, NC Plant) manufactures a black, continuous, (rolls/sheets) closed cell, 4.0 - 10 lb/ft<sup>3</sup> (64 - 160 kg/m<sup>3</sup>) density, PVC/NBR/CR rubber product IR41, that meets the requirements of ASTM D 1056 2A1/2C1/2B1. IR41 has excellent resistance to oil and fuel. IR41 meets the horizontal burn/flame requirements of FMVSS 302 at 0.125" (1/8") (3.18 mm) & higher. IR41 is listed to UL94 HBF at 6 mm (0.236") & higher (UL File# QMTR2.E520115). IR41 is listed with UL to UL50E [periodic & continuous compression] (UL File# UL File # JMST2.MH30018).

### TECHNICAL DATA SHEET | ROLLS/SHEETS (effective 29MAR21)

#### POLYMER: NBR/PVC/CR

Physical Property	Test Method	Unit	Value
ASTM D 1056 Designation	-	-	2A1/2C1/2B1
Cell Structure	-	-	Closed
Color	-	-	Black
Compression Deflection 25%	ASTM D 1056	psi kPa	2* - 7* 13.8* - 48.3*
Compression Deflection 25%, after Heat Aging	ASTM D 1056	%	± 30
Compression Set (Room temp)	ASTM D 1056	%	25 max
Density	ASTM D 1056	lb/ft <sup>3</sup> kg/m <sup>3</sup>	4* - 10* 64.1* - 160*
Elongation	ASTM D 412 (Die A)	%	100 min
Flammability	FMVSS 302	in mm	0.125 and higher 3.18 and higher
Fluid Immersion	ASTM D 1056	%	100 max
Hardness, Durometer Shore 00	ASTM D 2240	-	30 - 50
Service Temperature	ASTM D 1056	°F °C	-40 -40
	Low		
	High Intermittent	°F °C	200 93.3
Tear Strength	ASTM D 624 (Die C)	lb/in kN/m	12 min 2.1 min
Tensile Strength	ASTM D 412 (Die A)	psi kPa	50 min 345 min
Water Absorption	ASTM D 1056	%	10 max

UL Listed to: UL94 (Flame) HBF (UL file# QMTR2.E520115) at 6.0 mm minimum thickness

\* Thicknesses ≤ 0.25" (6.35 mm) the 25% CD is 2 - 7 psi (13.8 - 48.3 kPa) & the Density is 4 - 10 lb/ft<sup>3</sup> (64.1 - 160 kg/m<sup>3</sup>)  
Thicknesses > 0.25" (6.35 mm) the 25% CD is 2 - 5 psi (13.8 - 34.5 kPa) & the Density is 4 - 7 lb/ft<sup>3</sup> (64.1 - 112 kg/m<sup>3</sup>)

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2021. All rights reserved. Trademarks followed by © or TM are trademarks of the Armacell Group.  
EnsoLite IR41 | DataSheet | 062021 | NA | EN-A

## ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,000 employees and 23 production plants in 15 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:

[www.armacell.us](http://www.armacell.us)

[info.cf.us@armacell.com](mailto:info.cf.us@armacell.com)

800-973-0490

