

TECHNICAL DATA SHEET (effective 12FEB20)

Armacell (EnsoLite[®]) OER Continuous Rolls/Sheets

Polymer: NBR/PVC

Physical Property	Test Method	Unit	Requirement
ASTM D 1056 Designation	---	---	2A1 / 2C1
Change in Compression Deflection	ASTM D 1056	%	±30
Color	---	---	Black
Compression Deflection 25%	ASTM D 1056	psi kPa	2.0 - 5.0 13.8 - 34.5
Compression Set (Room temp)	ASTM D 1056	%	40 max
Density	ASTM D 1056	lb/ft ³ kg/m ³	3.0 - 6.0 48.06 - 96.11
Elongation	ASTM D 412 Die A	%	100 min
Fire/Smoke Properties @ 1" thickness or less	ASTM E 84	Flame Spread Index/Smoke Developed Index	25/50
Fluid Immersion	ASTM D 1056 Reference Fuel B	%	250 max
Tensile Strength	ASTM D 412 Die A	psi kPa	15 min 103.4 min
Water Absorption	ASTM D 1056	%	10 max

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the Armacell General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.

© 2020 Armacell EnsoLite[®] is a registered trademark of the Armacell Group.

For more information:
www.armacell.us
info.cf.us@armacell.com
 800-973-0490