

FillPro Hot Rod XL

FillPro® Hot Rod XL Backer Rod (formerly ITP Hot Rod XL) is an extruded round, closed-cell, low-density polyethylene foam material which has been specially crosslinked to withstand temperatures in excess of 400°F (204°C). It is chemically inert and will resist oil, gasoline and most other solvents. The material will not stain, absorb moisture, nor adhere to sealant materials and is non-exuding.

www.armacell.us



APPLICATIONS

FillPro Hot Rod XL backer Rod is a backup material for most hot-pour sealants used to fill contraction and expansion joints of concrete highways, runways, driveways, and parking lots.

BENEFITS

FillPro Hot Rod XL is an ideal non-absorbent backer rod used to control high temperature sealant depth and create a back stop to allow proper wetting of the joint surfaces and yield a proper bond breaker between the backer rod and the sealant. Limiting the depth of the sealant prevents excessive use, saving on caulk or sealant. Hot Rod XL backer rod can also be used as a temporary joint seal.

INSTALLATION

The joint depth must be great enough to allow for the proper installation of the Hot Rod XL bond breaker and hot pour sealant. The joint width will be determined by the appropriate thermal expansion coefficient as released to anticipated temperature variances. Joint walls must be smooth, even and be free of any loose residues or foreign materials. Joints should also be dry and frost-free. Using Proper Sizing Chart on reverse side, select the proper rod diameter and cut length or use directly from spool. With a correctly-sized rubber tool, blunt instrument or by hand, install rod at the level recommended by the sealant manufacturer, specifier or government agency involved.

FEATURES:

- // Closed-cell, non-absorbent
- // Chemically inert
- // Resistant to oil, gas and other solvents
- // Use with hot pour sealants up to 400°F (204°C)
- // Made in Canada
- // ASTM D5249 Type 1

COMPATIBLE WITH:

- // Most rubber-asphalt and coal tar-rubber polymer thermoplastic compounds

STOCKED OPTIONS:

- // Available in beige in a wide variety of diameters (See reverse side)



TECHNICAL DATA – FillPro® Hot Rod XL Backer Rod (Formerly ITP Hot Rod XL)

Description

Flexible beige, closed-cell crosslinked polyethylene foam backer rod in continuous coils and 6 foot lengths.

Typical Properties

Property	Value	Test Method
Density (nominal)	1.5 - 2.5 lbs/cu.ft	ASTM D1622
Outgassing (# of bubbles)	>1	ASTM C1253
Tensile Strength psi (kPa)	16 PSI minimum	ASTM D1623
Compression Recovery, %, min	>96	ASTM D5249
Compression Deflection psi (kPa)	5.8 (39.9)	ASTM D5249
Water Absorption	0.03 gm/cc	ASTM C1016
*Temperature Range (maximum)	392°F	ASTM D5249
Classification	Type 1	ASTM D5249

*A well-known and widely employed rubber asphalt sealing compound was employed at various temperatures between 390°F and 410°F

Sizes

Diameter	Shipping Format	Feet Per Carton	Metric Diameter	Meters Per carton
3/8"	1 Spool	2100	9 mm	640
1/2"	2 Spools	2500	12 mm	762
5/8"	2 Spools	1550	15 mm	472
3/4"	1 Spool	1100	19 mm	335
7/8"	1 Spool	850	22 mm	259
1"	1 Spool	600	25 mm	182
1-1/4"	1 Spool	400	31 mm	121
1-1/2"	6' Lengths	396	38 mm	121
2"	6' Lengths	228	50 mm	70

Carton Sizes and Weights

Rod Diameter	Weight Per Carton	Cartons Per Skid	Carton Measurement
3/8"	6 lbs	36	18" x 18" x 15"
9 mm	2.7 kgs		457 mm x 457 mm x 381 mm
1/2" - 1-1/4"	11 lbs	18	18" x 18" x 30"
12 mm to 31 mm	5 kgs		457 mm x 457 mm x 762 mm
1-1/2" - 2"	14 lbs	20	17" x 10" x 74"
38 mm to 50 mm	6.4 kgs		432 mm x 254 mm x 1880 mm

Proper Sizing Chart (Size to Joint Width)

Joint Width	Use Rod Diameter
3/16" - 1/4"	3/8"
1/4" - 3/8"	1/2"
3/8" - 1/2"	5/8"
5/8" - 3/4"	7/8"
3/4" - 7/8"	1"
7/8" - 1"	1-1/4"
1" - 1-1/4"	1-1/2"
1-1/4" - 1-1/2"	2"

Shipping Information

- // Rectangular cartons with convenient hand holes for carrying, are ideal for warehousing and handling.
- // Most other express services will accept all cartons for reshipment.
- // Truckload quantities furnished on pallets and may be warehoused 2 pallets high to maximize space.

For metric joint widths under 25 mm, it is recommended that Backer Rod be at least 3 mm larger.

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the Armacell General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.

© Armacell, 2019 00133 | Armacell | FillPro Hot Rod XL | Data Sheet | 112019 | NA | EN-NA | 5431

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,100 employees and 24 production plants in 16 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.



For more information, please visit:
www.armacell.us