## DESIGNED FOR DURABILITY

# Monarch® 3942

DIE EJECTION Closed cell 100% EPDM foam in bun form

// ASTM D 1056 2A2

// Manufactured in buns (blocks)

// Medium density expanded rubber

// Color gray

www.armacell.us













#### MONARCH 3942 | DIE EJECTION Closed cell 100% EPDM foam in bun form

Monarch 3942: Armacell (Spencer, WV Plant) manufactures a gray, closed cell, medium density 10 - 14 lb/ft³ (160 - 224 kg/m³) 100% EPDM rubber product 3942, that meets the physical property requirements of ASTM D 1056 2A2. 3942 has excellent resistance to ozone and elevated temperatures. 3942 does not incorporate a flame retardant but meets the horizontal burn / flame requirements of FMVSS 302 at 4.76 mm (0.188") (3/16") and higher. 3942 has high resilience / rebound characteristics.

#### TECHNICAL DATA SHEET | BUNS (effective 26FEB21)

| Physical Property                            |                   | Test Method        | Unit            | Value                               |
|--|-------------------|--------------------|-----------------|-------------------------------------|
| ASTM D 1056 Designation                      |                   | <del>-</del>       |                 | 2A2                                 |
| Cell Structure                               |                   |                    |                 | Closed                              |
| Color  |                   |                    |                 | Gray                                |
| Compression Deflection 25%                   |                   | ASTM D 1056        | psi<br>kPa      | 5 - 9<br>34.5 - 62                  |
| Compression Deflection 25%, after Heat Aging |                   | ASTM D 1056        | %               | <u>+</u> 30                         |
| Compression Set (Room temp)                  |                   | ASTM D 1056        | %               | 25 max                              |
| Density                                      |                   | ASTM D 1056        | lb/ft³<br>kg/m³ | 10 - 14<br>160 - 224                |
| Elongation                                   |                   | ASTM D 412 (Die A) | %               | 125 min                             |
| Flammability                                 |                   | FMVSS 302          | in<br>mm        | 0.188 and higher<br>4.76 and higher |
| Hardness, Durometer Shore 00                 |                   | ASTM D 2240        |                 | 50 - 70                             |
| Resilience                                   |                   | ASTM D 2632        | %               | 48 - 58                             |
|  | Low               | ASTM D 1056        | °F<br>°C        | -70<br>-56.6                        |
| Service Temperature                          | High Continuous   |                    | °F<br>°C        | 220<br>104.4                        |
|  | High Intermittent |                    | °F<br>°C        | 250<br>121                          |
| Tear Strength                                |                   | ASTM D 624 (Die C) | lb/in<br>kN/m   | 10 min<br>1.8 min                   |
| Tensile Strength                             |                   | ASTM D 412 (Die A) | psi<br>kPa      | 60 min<br>414 min                   |
| Water Absorption                             |                   | ASTM D 1056        | <del></del>     | 5 max                               |

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find ou about our processing of your data, please visit our Data Protection Policy.

© Armacell, 2021. All rights reserved. Trademarks followed by ® or TM are trademarks of the Armacell Group Monarch 3942 | DataSheet | 032021 | NA | EN-A

### **ABOUT ARMACELL**

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,200 employees and 24 production plants in 16 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

