


ENGINEERED FOR VERSATILITY

OleTex[®] CKJN 600 A

Closed cell PE crosslinked polyolefin foam in continuous rolls/sheets form

- // Chemically crosslinked
- // Tested per ASTM D 3575
- // Added flame retardant
- // Multiple colors available

www.armacell.us



 **armacell**[®]
ArmaComp[®]

OLETEX® CKJN 600 A | Closed cell PE crosslinked polyolefin foam in continuous rolls/sheets form

OleTex CKJN 600 A: Armacell (Yukon, OK Plant) manufactures a continuous, (rolls / sheets) closed cell, 5.5 - 6.5 lb/ft³ (88.1 - 104 kg/m³) density, PE crosslinked polyolefin foam product CKJN 600 A. CKJN 600 A contains an added flame retardant and meets the requirements of FMVSS 302 at 0.250" (1/4") (6.35 mm) & higher. CKJN 600 A is available in a variety of colors. ** This product is not intended for elevated temperature applications.

TECHNICAL DATA SHEET | ROLLS / SHEETS (effective 20DEC21)

POLYMER: PE

Physical Property	Test Method	Unit	Value	
Cell Structure	-	-	Closed	
Color	-	-	Multiple	
Compression Deflection 10%	ASTM D 3575 Suffix D	psi kPa	8 - 18.5 55.2 - 127	
Compression Deflection 25%	ASTM D 3575 Suffix D	psi kPa	14.5 - 24.5 100 - 168	
Compression Deflection 40%	ASTM D 3575 Suffix D	psi kPa	20.5 - 34 141 - 234	
Compression Deflection 50%	ASTM D 3575 Suffix D	psi kPa	29.5 - 43.5 203 - 299	
Compression Set (Room temp)	ASTM D 3575 Suffix B	%	TBD	
Density	ASTM D 3575 Suffix W	lb/ft ³ kg/m ³	5.5 - 6.5 88.1 - 104	
Elongation	ASTM D 3575 Suffix T	%	50 min	
Flammability	FMVSS 302	in mm	0.25 and higher 6.35 and higher	
Service Temperature	Low	-	°F °C	-65 -54
		High Intermittent	-	°F °C
Tear Strength	ASTM D 3575 Suffix T	lb/in kN/m	78 min 13.7 min	
Tensile Strength	ASTM D 3575 Suffix T	psi kPa	100 min 689 min	
Thermal Stability	ASTM D 3575 Suffix S	%	TBD	
Water Absorption	ASTM D 3575 Suffix L	lb/ft ²	0.1 max	
		kg/m ²	0.5 max	

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2022. All rights reserved. Trademarks followed by © or TM are trademarks of the Armacell Group.
OleTex CKJN 600 A | DataSheet | 012022 | NA | EN-A

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,000 employees and 23 production plants in 15 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:

www.armacell.us

info.cf.us@armacell.com

800-973-0490

