

TECHNICAL DATA SHEET (effective 20JUL20)

Armacell (OleTex[®]) CKJT 600 Continuous Rolls / Sheets

Polymer: Polyethylene

Physical Property	Test Method	Unit	Value
Cell Structure	-	-	Closed Cell
Color	-	-	Various
Compression Deflection 10%	ASTM D 3575 Suffix D	psi kPa	11.3 - 13.8 77.9 - 95.1
Compression Deflection 25%	ASTM D 3575 Suffix D	psi kPa	16.8 - 20.5 115.8 - 141.3
Compression Deflection 40%	ASTM D 3575 Suffix D	psi kPa	23.3 - 28.5 160.6 - 196.5
Compression Deflection 50%	ASTM D 3575 Suffix D	psi kPa	29.9 - 36.6 206.2 - 252.3
Compression Set (Room temp)	ASTM D 3575 Suffix B	%	TBD
Density	ASTM D 3575 Suffix W	lb/ft ³ kg/m ³	6.0 - 6.6 96.1 - 105.7
Elongation	ASTM D 3575 Suffix T	%	172 min
Flammability	FMVSS 302 @ 1/4" and thicker	mm/min	Pass
Tear Strength	ASTM D 3575 Suffix T	lb/in kN/m	34.6 min 6.1 min
Tensile Strength	ASTM D 3575 Suffix T	psi kPa	127.6 min 879.8 min
Thermal Stability	ASTM D 3575 Suffix S	%	10.1
Water Absorption	ASTM D 3575 Suffix L	lb/ft ² kg/m ²	0.1 0.5

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the Armacell General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.

© 2020 Armacell OleTex[®] is a registered trademark of the Armacell Group.

For more information:
www.armacell.us
info.cf.us@armacell.com
 800-973-0490